

**PATENT ABSTRACTS OF JAPAN**(11)Publication number : **59-153851**(43)Date of publication of application : **01.09.1984**

(51)Int.Cl.

**C22C 1/05****B22F 3/10****C22C 29/00**(21)Application number : **58-025514**(71)Applicant : **KURATOMI TATSURO**(22)Date of filing : **19.02.1983**(72)Inventor : **KURATOMI TATSURO****(54) PRODUCTION OF SINTERED BODY OF CUBIC BORON NITRIDE COMBINING ALUMINA AND TITANIUM NITRIDE**

(57)Abstract:

PURPOSE: To form a sintered body of cubic boron nitride provided with high hardness and strong resistance to oxidation by sintering a powder mixture composed of a specific ratio of cubic BN, Al<sub>2</sub>O<sub>3</sub>, TiN, Al, Si under specific temp. and pressure conditions.

CONSTITUTION: A mixture composed, by weight %, of 50W70 cubic BN powder, 20W10 Al<sub>2</sub>O<sub>3</sub> powder, 18W8 TiN powder, 8W10 Al powder, and 4W2 Si powder is packed in a vessel and is packed in a chamber for generating high temp. and high pressure. A pressure of 47,000W50,000kg/cm<sup>2</sup> is applied on the powder and the temp. is heated up to 1,500W1,600°C by gradual heating and is held at said temp. for 10W60min. The heating is stopped with the pressure held as it is and the chamber inside is cooled to decrease the temp. therein down to 300°C. The pressure held in the above-mentioned state is returned to atmospheric pressure and the sintered body is removed from the inside of the chamber. The titled sintered body having excellent performance as a cutting tool is thus obt'd.

**LEGAL STATUS**

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]